



Grupo Gevir

COK DOY

Fabricación de cok de fundición / Manufacture of foundry coke

	>140 mm y 90/140 mm	60/90 MM y 30/60 MM	10/30 MM	0/10 MM	
CARACTERÍSTICAS	HUMEDAD	<1%	<6%	<10%	<15%
	CENIZAS	<8%	<8%	<9%	<11%
	VOLATILES	<1%	<1,5%	<2%	<4%
	AZUFRE	<0,8%	<0,8%	<0,8%	<0,8%
	CARBONO FIJO	>91%	>90,5%	>89%	>85%
	POT CAL SUP	>7400 Kcal/kg	>7300 Kcal/kg	>7250 Kcal/kg	>7200 Kcal/kg
	M-80/M80	>75%			
	M-40/M40	>85%	>85%		
	M-10/M10	<10%	<10%		

CERTIFICADA EN CALIDAD ISO 9001 Foundry Coke

	>140 mm y 90/140 mm	60/90 MM y 30/60 MM	10/30 MM	0/10 MM	
SPECIFICATIONS	HUMIDITY	<1%	<6%	<10%	<15%
	ASH	<8%	<8%	<9%	<11%
	VOLATILE	<1%	<1,5%	<2%	<4%
	SULPHUR	<0,8%	<0,8%	<0,8%	<0,8%
	FIXED CARBON	>91%	>90,5%	>89%	>85%
	POT CAL SUP	>7400 Kcal/kg	>7300 Kcal/kg	>7250 Kcal/kg	>7200 Kcal/kg
	M-80/M80	>75%			
	M-40/M40	>85%	>85%		
	M-10/M10	<10%	<10%		

CERTIFIED WITH QUALITY ISO 9001 Foundry Coke